



GLOBAL JOURNAL OF RESEARCHES IN ENGINEERING: J
GENERAL ENGINEERING
Volume 18 Issue 3 Version 1.0 Year 2018
Type: Double Blind Peer Reviewed International Research Journal
Publisher: Global Journals
Online ISSN: 2249-4596 & Print ISSN: 0975-5861

Extraction of Natural Dye Collected from Outer Skin of Onion and it's Application on Silk Fabric

By Nurunnesa, Md. Alamgir Hossain & Md. Mahbubur Rahman
Northern University

Abstract- Due to eco-friendliness of natural dyes and the awareness among people regarding the environmental and health hazards associated with the use of synthetic dyes, the craze for the clothing dyed with natural dye is increasing day by day. The aim of the work is to produce a variety of shades on the silk fabric by using Onion (Allium cepa) outer skin with different types of mordants such as Alum, Copper Sulfate, and Potassium Dichromate. Three different techniques of mordanting (Pre-mordanting, Meta-mordanting, and Postmordanting) have applied. The color fastness properties of dyed materials have also analyzed. After assessment of color fastness, it was found satisfactory in some cases and improved in many cases. As Onion is available and cheap, it will be convenient to produce unique shades of silk fabric, and to produce trendy and fashionable garments.

Keywords: natural dye, allium cepa, extraction, mordanting, silk, color fastness.

GJRE-J Classification: FOR Code: 291899



Strictly as per the compliance and regulations of:



RESEARCH | DIVERSITY | ETHICS

Extraction of Natural Dye Collected from Outer Skin of Onion and it's Application on Silk Fabric

Nurunnesa^a, Md. Alamgir Hossain^a & Md. Mahbubur Rahman^b

Abstract- Due to eco-friendliness of natural dyes and the awareness among people regarding the environmental and health hazards associated with the use of synthetic dyes, the craze for the clothing dyed with natural dye is increasing day by day. The aim of the work is to produce a variety of shades on the silk fabric by using Onion (*Allium cepa*) outer skin with different types of mordants such as Alum, Copper Sulfate, and Potassium Dichromate. Three different techniques of mordanting (Pre-mordanting, Meta-mordanting, and Post-mordanting) have applied. The color fastness properties of dyed materials have also analyzed. After assessment of color fastness, it was found satisfactory in some cases and improved in many cases. As Onion is available and cheap, it will be convenient to produce unique shades of silk fabric, and to produce trendy and fashionable garments.

Keywords: natural dye, *allium cepa*, extraction, mordanting, silk, color fastness.

I. INTRODUCTION

Nowadays, the Environment pollution is emerging as an alarming issue all over the world. The textile industry regards as the most polluting, as water pollution caused by effluents. These effluents contain toxic chemicals like carcinogenic amines and mutagens in Azo dyes, heavy metals, formaldehyde, etc. [1]

Environmentalists are always concerned about the unbridled use of synthetic dyes in the textile industry as they cause water pollution and different problems related to waste disposal. [2]

In recent times, due to lower price and a wide range of bright shades with improved color fastness properties, synthetic dyes have been widely used as compared to natural dyes [3-4].

Natural dyes are experiencing a new beginning in the field textile coloration. They are more compatible with the environment compared to synthetic dyes because they are eco-friendly, non-toxic, non-allergenic and biodegradable. [5]

Natural dyes are colorants obtained from different natural sources without any synthesizing. It includes all the dyes derived from different natural sources such as plants, animals, and minerals. There are different types of natural dyes like henna, onion, turmeric, marigold, betel nut, etc. The roots, stems,

barks, leaves, berries, and flowers of various dye plants are continuously using for dyeing carpets, rugs, and clothing. Due to no substantivity of most of the natural dyes, it has to apply to the substrate with the help of different mordants. [6]

Even though Synthetic dyes have many benefits, it has one negative side which deluges all the benefits, and the negative side is that it is not compatible with our environment. It is the high time to reconsider the use of natural dyes. [7]

In this regards, many commercial dyers already have started using natural dyes as a convenient replacement of synthetic dyes to overcome the environmental damage caused by synthetic dyes. Also, synthetic dyes such as azo dyes are found to be carcinogenic. [8]

Natural dyes are capable of producing unique, uncommon, alleviating and soft shades as compared to synthetic dyes as well Onion (*Allium cepa*) is a vegetable used in our daily life for cooking food and widely cultivated around the world. Most onions cultivated contain about 89% water, 4% sugar, 1% protein, 2% fiber. Onion also contains different types of Vitamins like Vitamin B1, Vitamin B2, Vitamin B3, and Vitamin C; it also contains compounds such as phenolics and flavonoids as well as elements like iron, calcium, magnesium, manganese, and zinc. [9]

The skin of onion is not edible and considered as wastage. However, it contains a coloring pigment called "Pelargonidin" (3, 5, 7, 4 tetrahydroxyantocyanidol). The amount of this coloring pigment is found to be 2.25%, and the structural formula of it has shown in Figure-1. [10]




Figure 1: Structural Formula of Pelargonidin" (3, 5, 7, 4 tetrahydroxyantocyanidol)

Onion is cultivated all over the country but extensively cultivated in Faridpur, Dhaka, Rajshahi, Comilla, Jessore, Dinajpur, Mymensingh, Rangpur, and Pabna in Bangladesh. Onion has become an integral part of the people's daily diet, and its use is very typical in almost all food preparations in Bangladesh. Onion mainly uses as a spice in Bangladesh. The only edible portion of onion is the bulb whereas Onion skin is inedible. [11]

II. MATERIALS AND METHOD

a) Colorant and Substrate

Waste outer skin of Onion (*Allium cepa*) was brought from the local market and washed with water and then dried at room temperature. After that, the skin had meshed and extracted the color by heating with water at 60 degree Celsius temperature for one hour. Degummed silk fabric had used as a substrate for dyeing.

b) Chemicals and Machine

As chemicals Alum, Potassium dichromate, and Copper sulfate of different concentrations, and as the

machine the conventional sample (lab) dyeing machine had used for dyeing in this research.

c) Fastness properties

According to the ISO 105 C03 test method washing fastness of the dyed sample was done. The assessment of color fastness to rubbing was done by following ISO 105:12 test method.

d) Extraction Process of Onion

Extraction is usually used to recover a component either from a solid or liquid. The outer skin of onion can be extracted with water by heating. The collected outer skin of onion mixed with water, and heated for 60 minutes at 65 °C (degree Celsius) temperature. Finally, the liquid dye from the skin was separated by filtration. The process was repeated for the same solid material to extract the dye portion as much as possible. The extraction process curve of onion has shown in Figure-2.




Figure 2: Extraction Process Curve of Onion

e) Mordanting process

A mordant is a dye fixative and able to use for dyeing fabrics with natural dyes. The natural dyes have no substantivity to the substrate. Three types of mordanting techniques named pre-mordanting, meta-mordanting, and post-mordanting commonly used for the coloration of textile substrate with natural dyes. In pre-mordanting the substrate is treated with the mordant, and then dyed, in meta-mordanting, the mordant is added to the dye bath itself, and in post-mordanting, the dyed material is treated with the mordant.

In this experiment three types of mordants used with the different concentration of mordants and pre, meta, and post-mordanting techniques had applied. In

this experiment, 1% to 3% mordant used in all pre, meta and post-mordanting techniques.


f) Degumming of Silk Fabric

Silk fiber contains natural impurities called gum or sericin. This sericin is near about 20% of weight compared to the whole weight of Silk fiber. Besides this Silk fiber comprises some wax and natural colors. In this work, degumming had used to remove these materials by treating the substrate with soda ash.

Raw Silk fabric was degummed in according to the following recipe which is shown in Table-1, and the degummed fabric was washed with 2 g/l detergent at 65°C for 10 minutes. Also, the process curve for degumming of silk fabric has been shown in figure-3.

Table 1: Recipe for Degumming of Silk Fabric

Detergent	5 g/l
Soda ash	3 g/l
Sequestering agent	1 g/l
Wetting agent	1 g/l
M:L	1:20
Temperature	90°C
Time	60 minutes
pH	9

*Figure 3:* Process Curve for Degumming of Silk Fabric


g) Dyeing process

In the pre-mordanting technique, the pre-mordanted sample immersed in liquid extracted from the outer skin of Onion at a liquor ratio of 1:50. Then dyeing had done by the sample (lab) dyeing machine. It carried out for 60 minutes at 70 °C temperature, and the pH was around 6.0 in the dye bath. Then the dyed material was washed with cold water and dried at room temperature. Finally a dyed sample found.

For meta and post-mordanting the dyeing process was the same, but the mordant used in dye bath during dyeing for meta-mordanting, and after dyeing for post-mordanting. The recipe for dyeing of silk fabric with onion skin has shown in table-2. Also, the process curve for dyeing of silk fabric with onion skin has represented in figure-4.

Table 2: Recipe for Dyeing of Silk Fabric with Onion Skin









Silk fabric	1 g
Liquid dye	50 ml
Mordant	(1-3)%
M:L	1:50
Temperature	70°C
Time	60 minutes
pH	6

*Figure 4:* Process Curve for Dyeing of Silk Fabric with Onion Skin

III. RESULT AND DISCUSSION

a) Visual comparison

Table 3: Dyed Samples

Mordants	Conc. (%)	Pre-mordanted	Meta-mordanted	Post-mordanted
Alum	1			
	2			
	3			
$K_2Cr_2O_7$	1			
	2			
	3			
$CuSO_4$	1			
	2			
	3			

b) Color fastness to wash

Table 4: Assessment Result for Color Change

Sl. No.	Mordants	Pre-mordant	Meta-mordant	Post-mordant
1	Alum 1%	2	1	2
2	Alum 2%	3	2	2
3	Alum 3 %	4	3	3
4	CuSO_4 1%	2	1	2
5	CuSO_4 2%	3	2	3
6	CuSO_4 3%	4	3	3
7	$\text{K}_2\text{Cr}_2\text{O}_7$ 1%	3	3	3
8	$\text{K}_2\text{Cr}_2\text{O}_7$ 2%	3	4	4
9	$\text{K}_2\text{Cr}_2\text{O}_7$ 3%	2	4	4

Table 5: Assessment Result for Color Staining

Sl. No.	Mordants	Pre-mordant	Meta-mordant	Post-mordant
1	Alum 1%	4-5	4-5	4-5
2	Alum 2%	4-5	4-5	4-5
3	Alum 3 %	4-5	4-5	4-5
4	CuSO_4 1%	4-5	4-5	4-5
5	CuSO_4 2%	4-5	4-5	4-5
6	CuSO_4 3%	4-5	4-5	4-5
7	$\text{K}_2\text{Cr}_2\text{O}_7$ 1%	4-5	4-5	4-5
8	$\text{K}_2\text{Cr}_2\text{O}_7$ 2%	4-5	4-5	4-5
9	$\text{K}_2\text{Cr}_2\text{O}_7$ 3%	4-5	4-5	4-5

c) Color fastness to rubbing

Table 6: Assessment Result for Color Fastness to Rubbing

Sl. No.	Mordants	Dry/Wet	Pre-mordant	Meta-mordant	Post-mordant
1	Alum 1%	Dry	4-5	4-5	4-5
		Wet	4	4	4
2	Alum 2%	Dry	4-5	4-5	4-5
		Wet	4	4	4
3	Alum 3 %	Dry	4-5	4-5	4-5
		Wet	4	4	4
4	CuSO_4 1%	Dry	4-5	4-5	4-5
		Wet	4	4	4
5	CuSO_4 2%	Dry	4-5	4-5	4-5
		Wet	4	4	4
6	CuSO_4 3%	Dry	4-5	4-5	4-5
		Wet	4	4	4
7	$\text{K}_2\text{Cr}_2\text{O}_7$ 1%	Dry	4-5	4-5	4-5
		Wet	4	4	4
8	$\text{K}_2\text{Cr}_2\text{O}_7$ 2%	Dry	4-5	4-5	4-5
		Wet	4	4	4
9	$\text{K}_2\text{Cr}_2\text{O}_7$ 3%	Dry	4-5	4-5	4-5
		Wet	4	4	4

In this research, a variety shades of silk fabric produced by using the outer onion skin, shown in Table-3. Besides, it also found that for getting excellent shade, it must need to use different types of mordants. In this experiment, it has been tried to show that how different techniques of mordanting change the shades despite using the same mordant with the same concentration. Table- 6 shows color fastness to rubbing was very good for all the samples but color fastness to washing was not good for all that has shown in Table- 4. It also found that assessment result for color change was very good in case of the pre-mordanting technique for 3% Alum and 3% Copper sulfate, in meta-mordanting technique for both 2% and 3% Potassium dichromate and post-mordanting technique for 2% and 3% Potassium dichromate. The result was found to be good for color change in pre-mordanting technique for 2% Alum, 2% Copper sulphate, 1% and 2% Potassium dichromate, in meta-mordanting technique for 3% Alum, 3% Copper sulphate and 1% Potassium dichromate and in post-mordanting technique for 3% Alum, 2% and 3% Copper sulphate and 1% Potassium dichromate. Besides, it also found that assessment result for color staining was very good for all the samples which are very convenient for dyeing of silk fabric with Onion skin.

REFERENCES RÉFÉRENCES REFERENCIAS

1. NimkarUllhas and BhajekarRahul, Ecological requirements for the textile industry, Supplement to *Colourage*, LII (4), 135-142, (2006).
2. Ali, N.F., El-Mohamedy, R.S.R. and Rajput, S., Improvement of Antimicrobial Activity for Onion Natural Dyed Fabrics through Chitosan Pretreatment, *Journal of Applied Sciences Research*, 9, 4993-5002 (2013)
3. Iqbal, j.,Bhatti, I.,Adeel, S.,Effect of UV radiation on dyeing of cotton fabric with extracts of henna leaves, *Indian journal of Fibre & Textile Research*,33, pp. 157-162, (2008)
4. Alemanyehu, T.,Teklemariam, Z.,Application of Natural Dyes on Textile: A Review, *International Journal of Research - Granthaalayah*, 2 (2), pp. 61-68, (2014).
5. P. Saravanan1, G. Chandramohan, S. Saivaraj and D. Deepa, Extraction and application of eco-friendly natural dye obtained from barks of *Odinawodier*.L on cotton fabric, Scholars Research Library, 3 (2):80-85, (2013)
6. Gulrajani, M.L., Natural Dyes and Their Applications to Textiles, edited by Gulrazani M. L.,Gupta, D., IIT New Delhi, India,1-2,(1992)
7. Kulkarni, S.S., Gokhale. A.V., Bodake. U.M., Pathade. G.R., Cotton dyeing with Natural Dye Extracted from Pomegranate Peel, *Universal Journal of Environmental Research and Technology*,1(2), pp. 135-139,(2011)
8. Samanta, A.K. and Agarwal, P, Application of Natural Dye on Textiles, *Indian Journal of Fibre and Textile Research*, 34, 384-399, (2009)
9. Onal, A., Extraction of dyestuff from onion (*Allium cepa L.*) and its application in the dyeing of wool, feathered-leather and cotton, *Tr. J. of Chemistry*, (20) p. 194 – 203, (1996)
10. ShaliniChandrvanshi and Santosh K. Upadhyay, Interaction of Natural Dye (*Allium cepa*) with Iconic Surfactant, *Journal of Chemistry*, Volume 2013, Article ID 685679, (2013)
11. Hossain AK, Islam J. Status of Allium production in Bangladesh. *ActaHortic* 1994;358:33-6, (1994).